



Fabricated Glass Specialties, inc.

1-800-347-5952 * Fax: (541) 535-2910 * www.fabglass.com

Flaw Standards

In regards to ASTM Standards

Location of Inclusion Within Lite of Glass

	<u>Central</u>	<u>Outer</u>
Gaseous Inclusions	1/4"	1/2"
Open or Translucent Gaseous Inclusions	1/4"	1/4"
Knots, Dirt, and/or Stones	1/32"	1/16"
Scratches or Rubs	light	light
Crush	<1/4"	<1/2"
Digs	1/4"	1/2"
Ream, Strings, Lines or Linear Distortion	light	light
Wave	medium	medium
Process Surface Blemishes	medium	medium

Shadowgraph Distances

Reams, Strings, Lines or Linear Distortion	light	3 inches
Wave	medium	10 inches
Process Surface Blemishes	medium	

*Visible, when viewed in normal reflected light,
as a slight grayish haze.*

American Society For Testing And Materials. 1916 Race St. Philadelphia, PA 19103

This information based on ASTM Standards.

©Copyright ASTM

Information provided by Pilkington.

© Copyright 2004

Effective: 3/31/2004

Replaces: 12/1/2002